



2nd International Paris-Saclay Workshop on Nanodiamonds

October 13-15, 2025, ENS Paris Saclay



Abstract Book

université
PARIS-SACLAY

GRADUATE SCHOOL
Chimie

Institute for the
Sciences of Light

GRADUATE SCHOOL
Physique



iramis

Monday, October 13th

11h30-12h30	Registration	
12h30-14h00	<i>Lunch - Restaurant La Ruche</i>	
14h-14h15	Organizers	Workshop Introduction

Session 1: Color Centers in Nanodiamonds

14h15-14h50	O. Shenderova	Next-generation fluorescent nanodiamond for biological quantum sensing
14h50-15h10	V. Pugliese	Fabrication and opto-physical characterization of Magnesium-Vacancy color centers in nanodiamonds
15h10-15h30	S. Potocky	Scalable synthesis of SiV-doped nanodiamonds via bottom-up and top-down CVD approaches
15h30-15h50	M. de Feudis	Controlled HPHT annealing of SiV-doped nanodiamonds at SOLEIL synchrotron: structural and optical investigations
15h50-16h20	<i>Coffee Break</i>	

Session 2: Advanced Characterizations & Surface Chemistry

16h20-16h55	A. Chemin	Advanced characterizations of nanodiamonds by synchrotron-based techniques
16h55-17h15	J.C. Arnault	Extreme surface chemistry of isolated nanodiamonds probed by synchrotron X-ray photoemission
17h15-17h35	M. Dubois	Fluorination: a smart approach to designing high-value sp ³ carbon-based nanomaterials: diamane and ultrapure nanodiamonds
17h35-17h55	M. Finas	Nanodiamond band gap engineering: towards visible range photo activity

Tuesday, October 14th

Session 3: Nanodiamonds for Energy

9h-9h35	S. Orlanducci	Gold and Silver Decorated Nanodiamond are multifunctional nanoparticles for generating solvated electrons
9h35-9h55	D. Trucchi	Nanodiamond Technologies for High-Temperature Concentrated Solar Cells
9h55-10h15	A. Bellucci	Laser nanotextured diamond for sunlight conversion
10h15-10h35	H. Girard	Optimizing Nanodiamond Colloidal Suspensions: The Role of Surface Chemistry and Sonication Processes
<i>10h35-11h00</i>		<i>Coffee Break</i>

Session 4: Quantum Sensing

11h00 – 11h35	Q. Li	Spatially resolved temperature sensing in working electrochemical devices by nanodiamond quantum sensors
11h35-11h55	M. Techer	Thermal mapping of heterogeneous materials using NV centers in highly doped nanodiamonds.
11h55-12h15	B. Anezo	Sensing with NV- nanodiamonds : a spin active molecule and a metallic effect case
12h15-12h35	G. Jacopin	Time-Resolved Thermal Sensing using Nanodiamond Cathodoluminescence Spectroscopy
<i>12h35-14h30</i>		<i>Lunch - Restaurant La Ruche</i>

Session 5: Posters (to be completed)

14h30-16h00	N. Pham	Synthesis and surface functionalization of CVD nanodiamond containing SiV color centers for quantum sensor applications
	A. Kaga	Characterization of diamond electrodes with H-terminated N-doped nanolayers on B-doped films for CO ₂ reduction by electrochemical impedance spectroscopy
	D. Stanicki	Engineering Nanodiamonds for Enhanced EPR Imaging: Influence of Size, Surface Chemistry, and Paramagnetic Properties
	Y. Bouaouni	Surface-Modified Nanodiamonds for Enhanced Photocatalytic Hydrogen Generation
	A. Abi	Optical Communication via Rabi Oscillations in NV Center Ensembles
<i>16h00-16h30</i>		<i>Coffee Break</i>

Session 6: Synthesis of Nanodiamonds

16h30-16h50	A. Hoffman	Nanodiamond films formation from energetic species
16h50-17h10	S. Prasanna	Bottom-up production of nanodiamonds using MW microplasma
17h10-17h30	J. Jeevan	Improved gas phase nucleation of nanodiamonds with argon addition
17h30-17h50	R. Salerno	Etching of Nanodiamond Seeds during Early CVD Growth: Size-Dependent Modeling and Implications for Ultrathin Diamond Film Engineering
<i>19h00-21h00</i>		<i>Conference Dinner</i>

Wednesday, October 15th

Session 7: Sensing & Bioapplications I

9h-9h35	M. Fujiwara	12C enriched Fluorescent Nanodiamonds for biomedical quantum sensing applications
9h35-9h55	B. Grimaud	Measuring axonal transport using neurotropic fluorescent nanodiamonds
9h55-10h15	M.-O. David	Nanodiamond Conjugates for Tracking Disease-Linked RNA-Binding Proteins
10h15-10h35	G. Urbinati	Fluorescent Nanodiamond-based delivery systems for mitochondrial targeting of bioactive molecules
10h35-11h00	Coffee Break	

Session 8: Sensing & Bioapplications II

11h00 – 11h35	Y.Y. Hui	Nanodiamond Scintillator: A Novel Approach to Profiling EUV and Soft X-ray Beams for Photolithography
11h35-11h55	Sturari Sofia	Surface tuning of nanodiamonds: investigating the impact of surface modifications for applications in radiosensitization
11h55-12h15	Wu Yingke	Precision Engineering of Immunocellular States via Intracellular Fever with Nanodiamond Composites
12h15-12h35	B. Ercolani	Hybrid Nanozyme Systems based on Gold-Decorated Nanodiamonds for Advanced Electrochemical Sensing and SERS substrate.
12h35-12h45	Organizers	Workshop Concluding Remarks
12h45-14h30	Lunch - Restaurant La Ruche	

Abstracts

Monday, October 13th
Sessions 1 & 2

Next-generation fluorescent nanodiamond for biological quantum sensing

Olga Shenderova^{*1}, Nicholas Nunn¹, Marco Torelli¹, and Antonin Marek¹

¹Adamas Nanotechnologies – United States

Abstract

Nitrogen-vacancy color centers in fluorescent diamond nanoparticles (NDNV) possess a uniquely coupled optical output related to their spin states, which, in turn, are highly sensitive to external fields and their local environment. This allows NDNV fluorescence to be selectively modulated through external electromagnetic fields, making diamond particles well-distinguishable in biological systems where high fluorescence background limits the use of other fluorophores. This capability is being advanced beyond background-free imaging to quantum sensing of local electromagnetic fields, free radicals, temperature, and pH with nanoscale resolution. The translational capability of such quantum sensors stems from improved sensitivity, resolution, and speed with respect to classical methods; however, successful implementation requires further fine-tuning of the NDNV material properties. One of the most impactful features in the design of quantum-grade NDNV is the substitutional nitrogen content, which needs to be an order of magnitude less than in commercially available starting particles typically used for production of NDNV for imaging applications. In parallel, the content of other parasitic paramagnetic impurities in the diamond lattice needs to be minimized. Finally, engineering of the particle surface states is required to stabilize the charge state of the NV centers. We discuss recent developments of fluorescent NDNV, including commercial synthesis of NDNV with low nitrogen content, annealing of particles at ultra-high temperature, including annealing at high (few GPa) pressure, and atmospheric plasma-based production of surface termination with negative electron affinity for NV charge stabilization. The outcome of these efforts is a pathway for production of next-generation nanodiamond particles adapted for quantum sensing applications as deployable biological sensors.

Funding Acknowledgements:

DOE DE-SC0022441

NIGMS 5R01GM143626

NIGMS 1R43GM155656-01

Keywords: fluorescent nanodiamond, nitrogen, vacancy centers, quantum sensing

^{*}Speaker

Fabrication and opto-physical characterization of Magnesium-Vacancy color centers in nanodiamonds

Vanna Pugliese^{*1,2}, Elena Nieto Hernández^{1,2}, Emilio Corte^{1,2}, Pietro Aprà², Sviatoslav Ditalia Tchernij^{1,2}, Paolo Olivero^{1,2}, and Jacopo Forneris^{1,2}

¹Department of Physics, University of Torino [Torino] – Italy

²Istituto Nazionale di Fisica Nucleare, Sezione di Torino – Italy

Abstract

Color centers in diamond are promising candidates for quantum technologies. The nitrogen-vacancy (NV) center is the most extensively studied, owing to its optically addressable spin state, which has enabled appealing pathways in quantum sensing and information processing. However, intrinsic limitations, such as broad spectral emission and relatively long radiative lifetime, can hinder its performance in certain quantum applications, motivating the exploration of new classes of color centers.

In this context, the magnesium-vacancy (MgV) center has recently emerged as a compelling alternative, featuring intense photoluminescence with a narrow zero phonon line (ZPL) and a shorter radiative lifetime (1). Additionally, the temperature dependence of MgV emission has been experimentally demonstrated and its strain sensitivity has been theoretically predicted (1,2)

In this work we report on the opto-physical characterization of these emitters embedded in nanodiamonds (20-100 nm), previously surface-treated to reduce external graphitic phases (3). The MgV centers were fabricated upon 50 keV MgH⁻ ion implantation and subsequent thermal annealing. A systematic photoluminescence investigation was performed at room temperature both at ensemble and at single-defect levels, comparing the results with MgV centers in bulk diamond. Single-emitter analysis revealed that MgV centers in nanodiamonds maintain radiative lifetimes comparable to their bulk counterparts, while exhibiting distinct spectral features. The fine structure observed in the ZPL (Fig.) is attributed to strain-induced effects, suggesting that internal stress in nanodiamonds could modulate the MgV centers emission.

These findings open new avenues for the exploitation of MgV centers and of their tunability at the nanoscale, highlighting the potential of strain engineering to control the optical properties and the spin state of this quantum emitter.

References

- E. Corte, *et al.* *ACS Photonics*, 10,1 (2023), 101–110
- A. Pershin, *et al.* *npj Quantum Information*, 7,1 (2021),99
- P. Aprà, *et al.* *Adv. Funct. Mater.*, 34, 39 (2024), 2404831

^{*}Speaker

Keywords: color centers, ion implantation, single photon sources, strain

Scalable synthesis of SiV-doped nanodiamonds via bottom-up and top-down CVD approaches

Štěpán Potocký^{*1}, Timea Melová^{1,2}, Zdeněk Doležal^{1,2}, Kateřina Aubrechtová Dragounová^{1,2}, Kateřina Kolářová¹, Štěpán Stehlík¹, Mario Agio³, and Alexander Kromka⁴

¹Institute of Physics of the Czech Academy of Sciences – Czech Republic

²Czech Technical University in Prague, Faculty of Nuclear Sciences and Physical Engineering – Czech Republic

³Laboratory of Nano-Optics, University of Siegen – Germany

⁴Institute of Physics of the Czech Academy of Sciences – Czech Republic

Abstract

Nanodiamonds (NDs) doped with silicon-vacancy (SiV) centers are emerging as versatile platforms for applications in quantum sensing, bioimaging, and photonics due to their stable and bright photoluminescence at room temperature. This study presents a comparative analysis of two complementary chemical vapor deposition based approaches for synthesizing SiV-doped NDs: a bottom-up (BU) employing porous diamond film growth followed by Si-doped overgrowth, and a top-down (TD) based on molten salt thermal etching of nanocrystalline diamond films. Both approaches result in brittle, porous diamond structures that are subsequently disintegrated into nanodiamonds using ultrasonic processing. Detailed morphological, structural, and optical characterizations confirm the successful incorporation of SiV centers with distinct spatial distributions and photoluminescence characteristics. The BU method yields core-shell-like NDs with surface-localized SiV centers, while the TD method yields homogeneous core-like doped NDs. Furthermore, temperature-resolved photoluminescence measurements reveal linear redshifts and broadening of the SiV zero-phonon line, demonstrating their potential for nanothermometry applications. These scalable fabrication routes offer a high-yield alternative to traditional methods, paving the way for the development of tailored nanodiamond materials in next-generation sensing technologies.

Keywords: nanodiamonds, silicon, vacancy centers, chemical vapor deposition, molten salt thermal etching, photoluminescence, nanothermometry

^{*}Speaker

Controlled HPHT annealing of SiV-doped nanodiamonds at SOLEIL synchrotron: structural and optical investigations

Mary De Feudis^{*1,2}, Kin On Ho³, Laura Henry⁴, Vanna Pugliese⁵, Boris Yavkin⁶, Marie-Pierre Adam⁶, Noemie Pham⁷, Nicolas Guignot⁴, Jean-Sébastien Lauret⁶, Fabien Bénédic⁸, Jocelyn Achard⁸, Philippe Goldner⁷, Serge Desgreniers⁹, and Jean-François Roch⁶

¹Institut de Recherche de Chimie Paris, Chimie ParisTech, UMR CNRS 8247, PSL Research University, 75005 Paris, France – PSL Université, Institut de Recherche de Chimie Paris, ChimieParisTech, UMR CNRS 8247, Paris, France – France

²CY Cergy Paris Université, 95031 Cergy-Pontoise, France – CY Cergy Paris Université – France

³Université Paris-Saclay, CNRS, ENS Paris-Saclay, CentraleSupélec, LuMIn, F-91190 Gif-sur-Yvette, France – Université Paris Saclay, ENS Paris Saclay, Centrale Supélec, CNRS – France

⁴Synchrotron SOLEIL, L'Orme des Merisiers, Saint-Aubin, 91192 Gif-sur-Yvette, France – Synchrotron Soleil – France

⁵University of Torino and Istituto Nazionale di Fisica Nucleare, sezione di Torino, 10125 Torino, Italy – Italy

⁶Université Paris-Saclay, CNRS, ENS Paris-Saclay, CentraleSupélec, LuMIn, F-91190 Gif-sur-Yvette, France – Université Paris Saclay, ENS Paris Saclay, Centrale Supélec, CNRS, France – France

⁷Institut de Recherche de Chimie Paris, Chimie ParisTech, UMR CNRS 8247, PSL Research University, 75005 Paris, France – PSL Université, Institut de Recherche de Chimie Paris, ChimieParisTech, UMR CNRS 8247, Paris, France – France

⁸Laboratoire des Sciences des Procédés et des Matériaux, UPR CNRS 3407, Université Sorbonne Paris Nord, 93430 Villetaneuse, France – Université Sorbonne Paris Nord, LSPM, CNRS, UPR 3407, Villetaneuse, France – France

⁹Laboratoire de physique des solides denses, Department of Physics, University of Ottawa, Ottawa, ON, K1N 6N5, Canada – Canada

Abstract

Diamonds and nanodiamonds (NDs) containing quantum color centers, such as nitrogen-vacancy (NV) centers, have been widely studied in recent years for their promising applications across various fields, including cryptography and telecommunications, medical sciences, and sensing. In the context of sensing, recent studies on color centers such as silicon-vacancy (SiV) and germanium-vacancy (GeV) centers have shown great potential for measuring physical quantities like magnetic fields, temperature, and strain. This is due to their intense zero-phonon line (ZPL) optical signal, about 80% of their total luminescence, which is characteristic of group-IV color centers (G4V) (1). In our recent papers, we demonstrated that

^{*}Speaker

as-grown CVD NDs containing SiV and GeV centers, featuring luminescent ZPLs and excellent photostability at room temperature, can function effectively as nanosensors of high stress and pressure conditions (up to 180 GPa) (2, 3). To advance our research, in this work we investigate the optical properties of SiV centers in as-grown NDs at cryogenic temperatures. For SiV centers, which have spin 1/2, the fine structure should become accessible through the Jahn-Teller effect, which lifts the degeneracy at cryogenic temperatures (< 20 K). However, experiments on our as-grown NDs reveal significant spectral broadening even at 9 K, caused by lattice strain, which prevents access to the optically addressable electronic spin states of the SiV center (see Fig.). To overcome this limitation, we propose an original post-treatment involving high-pressure and high-temperature (HPHT) annealing using the Paris–Edinburgh press. In fact, the gradual increase of temperature and pressure allows for control over the undesired diamond-to-graphite phase transition. HPHT annealing experiments were conducted at the PSICHE beamline of Synchrotron SOLEIL (4), where X-ray diffraction and tomography analyses enabled precise monitoring of P,T parameters and made it possible for the first time to access single fine-structure transitions of the in such SiV-NDs (see Fig.).

Figure. PL spectra of SiV-NDs before (orange line) and after (blue line) the HPHT annealing treatment registered at 9 K.

Keywords: HPHT annealing, SiV, doped nanodiamonds, SOLEIL synchrotron investigations

Advanced characterizations of nanodiamonds by synchrotron-based techniques

Arsène Chemin^{*1}

¹Institut Lumière Matière [Villeurbanne] – Université Claude Bernard Lyon 1, CNRS : UMR5306 – France

Abstract

Easy generation of solvated electrons from solar illumination represents a significant advancement for green chemistry and environmental applications. Diamond materials have been proposed as promising emitters of solvated electrons¹. Visible-light excitation could enable solar-driven CO or N reduction reactions in aqueous media.^{2,3} Recent developments in electrode design have shown increased activity even under visible light.⁴ However, sub-bandgap excitation remains challenging. Our recent studies have demonstrated that while sub-bandgap surface states can be excited in air, leading to charge separation and trapping,⁵ this does not necessarily translate to photocurrent generation in electrolytes.⁶ Therefore, a thorough investigation of the excitation pathways at the interface is required to engineer new materials.

In this work, we explore the strategy of functionalizing nanodiamonds with transition metal dyes to facilitate visible-light excitation of solvated electrons. Using soft X-ray spectroscopy techniques, we discuss the role of surface modifications on nanodiamond surface states and charge transfers at the interface between the nanodiamond and the electrolyte. These results open new perspectives for solar-driven emission of solvated electrons in aqueous phases using nanodiamonds.

(1) F. Buchner, T. Kirschbaum, A. Venerosy, H. Girard, J.-C. Arnault, B. Kiendl, A. Krueger, K. Larsson, A. Bande, T. Petit, C. Merschjann, *Nanoscale* 2022, 14, 17188-17195.

(2) P. Knittel, F. Buchner, E. Hadzifejzovic, C. Giese, P. Quellmalz, R. Seidel, T. Petit, B. Iliev, T. J. S. Schubert, C. E. Nebel, J. S. Foord, *ChemCatChem* 2020, 12, 5548.

(3) D. Zhu, L. Zhang, R. E. Ruther, R. J. Hamers, *Nat. Mater.* 2013, 12, 836.

(4) Yoshikawa, T., Kaga, A., Ichikawa, K., Hayashi, K., Matsumoto, T., Izumi, R., ... & Asakawa, H. 2025, *Electrochimica Acta*, 146058.

(5) Chemin, A., Levine, I., Rusu, M., Vaujour, R., Knittel, P., Reinke, P., ... & Petit, T. 2023. *Small Methods*, 7(11), 2300423.

(6) Chemin, A., Godeffroy, L., Rusu, M., Drisch, M., Finze, M., Knittel, P., ... & Petit, T, preprint, 2025 (10.26434/chemrxiv-2025-47rf0)

^{*}Speaker

Keywords: Diamonds, Surface, Interface, X, ray absorption spectroscopy, X, ray Photoemission Spectroscopy, Photoexcitation, Charge Transfers

Extreme surface chemistry of isolated nanodiamonds probed by synchrotron X-ray photoemission

Hugues Girard^{*1}, Marie Finas¹, Lorris Saoudi¹, Florent Ducroz¹, Marc Briant¹, Olivier Sublemontier¹, Aleksandar Milosavljevic², Christophe Nicolas², and Jean-Charles Arnault¹

¹Université Paris-Saclay, CEA, CNRS, NIMBE, 91191 Gif sur Yvette, France – CEA NIMBE – France

²Synchrotron SOLEIL – Centre National de la Recherche Scientifique, Centre National de la Recherche Scientifique : UR1 – France

Abstract

Nanodiamonds (ND) are currently under active investigation for their valuable and combinable properties in the fields of energy, quantum applications and nanomedicine^{1–3}. ND inherits its semiconducting behavior from bulk diamond. The surface chemistry strongly governs the physicochemical properties of ND: band structure, interaction with solvents in colloids, photoluminescence of hosted color centers. To shine a light on these different properties of ND, especially the photoreactivity of ND suspended in water under illumination, an investigation of their extreme surface chemistry is required to appreciate the real interface formed with water molecules when ND are in colloidal suspension.

At the PLEIADE beamline (SOLEIL synchrotron), a jet of isolated (or slightly aggregated) nanoparticles is produced from an aqueous colloid through a nebulizer and an aerodynamic lens⁴. The jet of nanoparticles intersects the synchrotron photon beam and emitted photoelectrons are then analyzed in energy. The energy of the incident photons can be adjusted to probe the extreme surface of the nanoparticles (a few tenth of nm for diamond) by X-ray photoelectron spectroscopy (XPS). The present study compares the extreme surface chemistry for isolated hydrogenated and oxidized milled nanodiamonds (MND) suspended in jets. The combination of synchrotron XPS data with conventional XPS results allowed us to build band diagrams for both milled nanodiamonds. A negative electron affinity (NEA) is obtained for H-MND whereas the affinity turned to positive for Ox-MND. As a comparison, hydrogenated DND were analyzed in the same experimental conditions.

References

- (1) H. Wang and Y. Cui, *Carbon Energy*, 2019, **1**, 13–18.
- (2) Y. Wu and T. Weil, *Adv. Sci.*, 2022, **9**, 1–19.
- (3) K. P. Loh et al., *Adv. Mater.*, 2018, **30**, 1–21.
- (4) O. Sublemontier et al., *J. Phys. Chem. Lett.*, 2014, **5**(19), 3399–3403.

Keywords: nanodiamonds, XPS, surface chemistry

^{*}Speaker

Fluorination: a smart approach to designing high-value sp^3 carbon-based nanomaterials-diamane and ultrapure nanodiamonds

Marc Dubois^{*1}, Killian Henry², Nicolas Batisse³, Brigitte Vigolo², Valery Nesvizhevsky⁴, and Sam Chen⁵

¹Université Clermont Auvergne – Université Clermont Auvergne, CNRS, Institut de Chimie de Clermont-Ferrand, F-63000 Clermont-Ferrand, France – France

²Institut Jean Lamour – CNRS, Institut Jean Lamour (CNRS – Université de Lorraine) – France

³Université Clermont Auvergne – Institut de Chimie de Clermont-Ferrand – France

⁴Institut Laue-Langevin – Institut Laue-Langevin (ILL), Grenoble, France – France

⁵University of Newcastle – Australia

Abstract

Most studies on fluorinated (nano)carbons focus on gas/solid treatment of sp^2 hybridized materials (graphite, graphene, nanotubes, fullerenes). The aim is to functionalize the bulk or surface for applications in energy storage, lubrication, band gap engineering, hydrophobicity, or composites. Carbon materials with sp^3 hybridization are less explored for gas/solid fluorination. The low reactivity of diamond carbons with elemental fluorine is valuable for high-value applications. Fluorinating detonation nanodiamonds (NDs, 4-5 nm) removes the sp^2 carbon shell and hydrogenated impurities (COH, COOH, CH). Chlorination of metallic impurities gives ultrapure NDs, ideal as neutron reflectors. Fluorine enhances stability in air, shifting decomposition temperature by 200°C. Fluorine also delays diamond-to-graphite conversion, similar to diamane, a bilayer of diamond carbons. Diamane is metastable at ambient temperature and pressure without stabilization by heteroelements (Cl, H, F) or hydroxyl groups (-OH). Fluorine is essential for preparing diamane, including exfoliation of fluorinated graphite $(\text{C}_2\text{F})_n$, which consists in stacked fluorinated diamane. Fluorine-stabilized diamane are promising in optical and photonic applications like lenses, coatings, and waveguides. Diamane, like diamond, is an excellent insulator with high dielectric strength. Its hardness and stability under extreme conditions offer advantages over other materials. Fluorine-stabilized sp^3 hybridized materials present a promising synthesis route, as controlled defluorination may induce partial graphitization. This allows preparation of ultrapure nanodiamonds with a perfect sp^2 carbon shell, functionalized for heterogeneous catalysis under harsh conditions (e.g., high-temperature HF reactions). The core-shell structure, with a stable diamond core and functionalized sp^2 carbon shell, enables well-controlled catalytic sites with enhanced stability.

Keywords: Fluorination, diamane, thermal stability

^{*}Speaker

Nanodiamond band gap engineering: towards visible range photo activity

Marie Finas^{*1}, Hugues Girard¹, Delphine Neff², Christophe Colbeau-Justin³, and Jean-Charles Arnault¹

¹Nanosciences et Innovation pour les Matériaux, la Biomédecine et l'Energie, UMR CEA-CNRS 3685 – CEA, CNRS, Université Paris-Saclay, CEA Saclay 91191 Gif sur Yvette France – France

²LAPA, NIMBE-IRAMAT, CEA, CNRS, Université Paris Saclay, 91191 Gif sur Yvette, France – NIMBE UMR3685 CEA/CNRS – France

³Institut de Chimie Physique – Université Paris-Saclay, Centre National de la Recherche Scientifique, Centre National de la Recherche Scientifique : UMR8000 – France

Abstract

Nanodiamonds are gaining attention as cutting-edge materials for photocatalysis. While their wide band gap might seem like a limitation, their highly tunable band structure, strongly governed by their surface chemistry, unlocks possibilities for critical reactions, such as CO₂ reduction¹ or PFAS degradation². Initially, photocatalytic activity was demonstrated under UV light^{1,2}, but recent breakthroughs involving our team revealed their potential under visible light^{3,4}. To push visible light photoactivity further, enhancing light absorption is key. A promising approach lies in embedding new graphitic energy states into the band gap, enabling the absorption of lower-energy photons³.

Band gap engineering, involving the introduction of intermediate energy levels, can be achieved through the formation of sp²-hybridized carbon surface reconstructions. Well-controlled graphitization of highly crystalline nanodiamond offers the potential to incorporate sp² carbon on the surface while maintaining the integrity of the diamond crystalline core.

We achieved controlled graphitization of nanodiamonds by annealing at low pressure within a temperature range of 800–1100°C. The resulting nanodiamonds were characterized using XRD, XPS, and Raman spectroscopy, confirming the formation of sp²/sp³ hybrids and revealing that the sp² content increases with rising temperature. Further analyses using HR-TEM and multi-wavelength Raman spectroscopy demonstrated that the surface reconstructions are highly dependent on particle size. Nanodiamonds were sorted prior to graphitization following a protocol previously developed⁵. The enhanced visible absorption of graphitized nanodiamonds was validated through Time Resolved Microwave Conductivity (TRMC) measurements that allow to investigate the dynamics of charge carriers under laser illumination. Nanodiamonds were illuminated from 290 to 500 nm, enabling the evaluation of the number and mobility of charge carriers within this wavelength range.

References

1. Zhang L et al. *Diam Relat Mater.* 2017;78:24-30. doi:10.1016/j.diamond.2017.07.005

^{*}Speaker

2. Maza WA et al. *Appl Catal B Environ.* 2023;325. doi:10.1016/j.apcatb.2022.122306
3. Buchner F et al. *Nanoscale.* Published online 2022:17188-17195. doi:10.1039/d2nr03919b
4. Marchal C et al. *Adv Energy Sustain Res.* Published online December 28, 2023. doi:10.1002/aesr.202300260
5. Finas M et al. *Nanoscale Adv.* Published online 2024:5375-5387. doi:10.1039/d4na00487f

Keywords: nanodiamonds, surface chemistry, TRMC

Tuesday, October 14th
Sessions 3 & 4

Gold and Silver Decorated Nanodiamond are multifunctional nanoparticles for generating solvated electrons.

Orlanducci Silvia^{*1}

¹Dipartimento di Scienze e Tecnologie Chimiche, Università degli Studi di Roma Tor Vergata [Roma, Italia] = University of Rome Tor Vergata [Rome, Italy] = Université de Rome Tor Vergata [Rome, Italie] – Italy

Abstract

Gold nanoparticles (AuNPs) and nanodiamonds (NDs) are extraordinary multifunctional nanomaterials with unique properties and a wide range of potential applications. The teamwork between AuNPs and NDs is related to the ability to control the shape and size of gold nanoparticles on the surface of nanodiamonds, modulate the colloidal properties, and their mutual interaction. This hybrid system can exhibit distinct catalytic and sensing activities, as both components contribute to these capabilities. Recently, it has been demonstrated that this system can efficiently generate solvated electrons using visible light, paving the way for numerous catalytic and synthetic applications. Similar findings were observed with silver-decorated ND particles. This lecture will discuss the synthetic approach for formulating hybrid nanosystems AuNPs-NDs and AgNPs-ND, as well as their structure, morphology, and efficiency in generating the solvated electrons.

S. Orlanducci et al, ACS Applied Optical Materials 2024, 2, 6, 1180-1187 DOI: 10.1021/acsaom.4c00132

S. Orlanducci, EurJIC- European Journal of Inorganic Chemistry- 2018, 48, 5138-5145 DOI: 10.1002/ejic.201800793

Keywords: gold nanoparticles, silver nanoparticles, Nanodiamonds, solvated electrons.

^{*}Speaker

Nanodiamond Technologies for High-Temperature Concentrated Solar Cells

Daniele Trucchi^{*1}, Raffaella Salerno^{*}, Alessandro Bellucci^{*2}, Eleonora Bolli, Riccardo Polini^{*3}, and Matteo Mastellone⁴

¹Consiglio Nazionale della Ricerche [Roma] – Italy

²Istituto di Struttura della Materia del Consiglio Nazionale delle Ricerche (ISM-CNR) – Italy

³Università degli Studi di Roma "Tor Vergata", Dip.to di Scienze e Tecnologie Chimiche (STC) – Via della Ricerca Scientifica 00133 Roma, Italy

⁴Institute of Structure of Matter of National Research Council (ISM-CNR) – Italy

Abstract

High-temperature solar cells and thermal energy converters are feasible by exploiting temperature-driven mechanisms, such as thermionic-thermoelectric generation (1), thermionic-photovoltaic conversion (2, 3), and photon-enhanced thermionic emission (PETE) concept, which represent novel and promisingly efficient (> 40%) mechanisms for the exploitation of concentrated sunlight. More advanced PETE converters rely on the concept that engineered nanodiamond photocathodes can provide an efficient electron emission, obtained by a synergistic combination of photogeneration and thermionic emission.

Two nanodiamond-based conversion technologies are pursued:

- 1) fs-laser nanotextured diamond as photoelectronically active material in black diamond PETE cathodes (4);
- 2) ultra-thin nanodiamond films grown on silicon absorbers in heterostructured PETE cathodes (5).

Results under a high-flux solar simulator are reported and discussed by demonstrating for the first time the PETE conversion at temperatures from 300 to 525 °C.

(1) D. M. Trucchi *et al.*, "Solar Thermionic-Thermoelectric Generator (ST2G): Concept, Materials Engineering, and Prototype Demonstration," *Advanced Energy Materials*, vol. 8, no. 32, 2018, doi: 10.1002/aenm.201802310.

(2) A. Bellucci *et al.*, "Photovoltaic Anodes for Enhanced Thermionic Energy Conversion," *ACS Energy Letters*, vol. 5, no. 5, pp. 1364-1370, 2020, doi: 10.1021/acsenenergylett.0c00022.

(3) A. Bellucci, P. García-Linares, A. Martí, D. M. Trucchi, and A. Datas, "A Three-Terminal Hybrid Thermionic-Photovoltaic Energy Converter," *Advanced Energy Materials*, vol. 12, no. 20, 2022, doi: 10.1002/aenm.202200357.

^{*}Speaker

- (4) D. M. Trucchi *et al.*, "Concentrated solar energy conversion by black-diamond photon-enhanced thermionic cathodes," *Submitted to Advanced Energy Materials*, 2025.
- (5) R. Salerno *et al.*, "Low electron affinity silicon/nanocrystalline diamond heterostructures for photon-enhanced thermionic emission", *ACS Applied Energy Materials* 7, 3 (2024) 868–873.

Keywords: Solar energy, electron emission, thermionic energy conversion

Laser nanotextured diamond for sunlight conversion

Alessandro Bellucci*¹

¹Istituto di Struttura della Materia del Consiglio Nazionale delle Ricerche (ISM-CNR) – Italy

Abstract

Diamond is completely solar-blind, and it cannot natively be applied for solar applications. To overcome this limitation, it has been proposed the use of diamond in thermionic-based converters, which are solid-state heat engine enabling the absorption of concentrated sunlight and transform it by the thermal emission and the collection of electrons. The application of a defect engineering strategy, that leads to the formation of nanotextured diamond with surface features below 200 nm, allows using freestanding diamond plates to be used as both solar receiver and electrons' emitting layer, i.e., in photon-enhanced thermionic emission (PETE). Such a strategy is enabled using ultra-short laser treatments, that are the key enabling technology for achieving this novel and disruptive concept. Additionally, this kind of structure has been proposed also for the hydrogen production by solar water splitting (SPEEDHY project, www.speedhy.it) since diamond represents a potential efficient source of solvated electrons in aqueous environment thanks to its chemical inertness and stability, and the wide electrochemical window. Finally, the laser technique can be potentially applied also to dope and functionalize nanodiamonds, for quantum and biomedical applications.

Keywords: ultra, short laser treatments, nanotexturing, electron emission.

*Speaker

Optimizing Nanodiamond Colloidal Suspensions: The Role of Surface Chemistry and Sonication Processes

Lorris Saoudi¹, Florent Ducrozet¹, Hugues Girard^{*1}, and Jean-Charles Arnault¹

¹Nanosciences et Innovation pour les Matériaux, la Biomédecine et l'Energie (NIMBE) – CEA, CNRS, Université Paris-Saclay – France

Abstract

In various applications, ranging from biomedicine to photocatalysis, nanodiamonds (NDs) have to be utilized in the form of aqueous colloidal suspensions to fully benefit from their extensive surface area. To achieve these colloidal suspensions, NDs must undergo ultrasound treatment, which serves to disaggregate the particles and stabilize them through their surface charge. However, the sonication process is complex and frequently overlooked in the literature, while it introduces sonochemical reactions that can significantly impact the final suspension in terms of concentration and composition. In this context, this study aims to investigate how the surface chemistry and characteristics of nanodiamonds influence the properties of the resulting colloid after a sonication process.

The first part of the study focuses on the proportion of nanoparticles that can be stabilized in colloidal suspension and how their surface chemistry influences this process. We evidence that, unlike other NDs, hydrogenated milled nanodiamonds (H-MND) exhibit an unusual behavior after successive sonication steps. Specifically, their concentration continues to increase after three sonication steps before decreasing to lower concentrations, following a more typical pattern. The mechanisms governing this particular resuspension behavior of H-MND in water are discussed, taking into account complementary characterizations of the colloids, including IR spectroscopy and Cryo-TEM (4).

Secondly, we show that sonication can generate nitrite and nitrate ions from dissolved N₂ (3). Sonicating water with oxidized detonation nanodiamonds (Ox-DND) increases nitrite production with higher concentrations, up to 15 $\mu\text{mol/L}$ in a 4 wt% solution, compared to 1 $\mu\text{mol/L}$ without Ox-DND. Surprisingly, H-DND do not show such an increase, raising questions about their interaction with the radicals formed during sonication. Our results also show that the formation of these species can be avoided in suspension by sonicating under a controlled atmosphere with no significant perturbation of ND colloidal stability or surface chemistry.

References

- (1) Saoudi, *Carbon*, 2023
- (2) Stehlik, *Carbon Trends*, 2024
- (3) Ducrozet, *J. Phys. Chem. C*, 2023
- (4) Saoudi, PhD, Paris Saclay University (2023)

^{*}Speaker

Keywords: Colloids, radicals, sonochemistry

Spatially resolved temperature sensing in working electrochemical devices by nanodiamond quantum sensors

Li Quan^{*1}

¹The Chinese University of Hong Kong – Hong Kong SAR China

Abstract

Temperature plays a crucial role in the operation of electrochemical devices, serving as both an indicator of device efficiency and stability. However, the complex material architecture within the device, coupled with local variations in electrochemical activity, leads to a time-dependent and spatially varying temperature at the nanoscale. Information on the spatially resolved temperature evolution is challenging due to the lack of non-invasive and accurate nano-thermometry methods that meet the requirements for sensitivity, spatial resolution, and temporal resolution within the reactive chemical environment of a functional device. In this presentation, I will discuss our recent progress in developing nanodiamond based thermometry to monitor the spatially resolved temperature evolution in operational electrochemical devices, including miniaturized battery cells and electrolyzers. We show that the local temperature within the working device, especially at the reaction interface, is considerably higher than the spatially averaged temperature measured from outside of the device using conventional methods. Spatial temperature variation has been found in conjunction with the respective electrochemical processes, disclosing the site sensitive chemical reactivity and its dynamics. Challenges in realizing the spatially resolved temperature sensing with adequate sensitivity and temporal resolution in these working devices will also be discussed in terms of the sensor quality and the device interface. This work is carried out in collaboration with Renbao Liu, Wenghang Leung, Ruqiang Dou, Zan Li, Hui Wang, Yao Gao, Ying Wang, and Chunyi Zhi. The authors acknowledge funding support from RGC CRF C4004-23G.

Keywords: nanodiamond, temperature sensing, electrochemical devices

^{*}Speaker

Thermal mapping of heterogeneous materials using NV centers in highly doped nanodiamonds.

Melissa Techer^{*1}, Boubacar Gandega¹, Marie-Pierre Adam¹, Mathieu Aurousseau², Loïc Toraille³, Kelly Wu⁴, Mark Hui⁴, Huan-Cheng Chang⁴, Denis Rochais², and Jean-François Roch¹

¹Ecole Normale Supérieure Paris-Saclay – Laboratoire Lumière, Matière et Interfaces – France

²CEA Le Ripault – Direction des Applications Militaires – France

³CEA/DAM [Arpajon] – Direction des Applications Militaires – France

⁴Academia Sinica – Taiwan

Abstract

Heterogeneous materials like carbon/carbon (C/C) composites consist of multiple microscopic constituents, whose temperature-dependent properties are often poorly characterized. This lack of precise data poses a challenge to numerical modeling, which relies on accurate micro-scale inputs to predict how individual parameters affect the overall thermal behavior of the material. Due to the small size of these constituents, conventional measurement techniques are inadequate. Until now only photoreflectance microscopy has provided the spatial resolution needed to accurately assess the thermal properties of a carbon fiber with a material volume of few cubic microns. However, photoreflectance does not determine the absolute temperature of the sample. Moreover, standard implementations rely on scanning a probe beam to record the change of the refractive index induced at the sample surface by a focused heating laser. This point-by-point analysis results in a long data acquisition time (typically a few hours).

To overcome these limitations, we have developed a thermal measurement bench using nanodiamonds highly doped with NV centers as thermal sensors. Due to the temperature dependence of its spin ground states, the NV center is a promising nanoscale thermal probe. This non-invasive method provides a direct measurement of the sample temperature while maintaining the high spatial resolution of the photoreflectance method.

We have optimized the deposition of the nanodiamonds to achieve a uniform and dense coverage of the sample surface. The temperature map on the sample surface is obtained by adapting NV widefield magnetic imaging which offers a multiplex advantage over scanning measurements. This significantly reduces the acquisition time (10 minutes for a field of view of 100 microns large). Initial measurements show a linear shift of the optically detected spin resonance frequency with increasing temperature, validating the use of NV centers as nanoscale thermal probes. Preliminary results were obtained on a test sample made of nitrocellulose fibers. These results pave the way for improved thermal imaging microscopy, especially for materials under extreme conditions.

^{*}Speaker

Sensing with NV- nanodiamonds : a spin active molecule and a metallic effect case

Bastien Anezo^{*1,2}, Izidor Benedičič², Gosar Žiga^{2,3}, Tanuma Yuri², Denis Arčon^{2,3}, and
Ewels Chris¹

¹Institut des Matériaux de Nantes Jean Rouxel – Centre National de la Recherche Scientifique, Nantes
université - UFR des Sciences et des Techniques – France

²Jozef Stefan Institute [Ljubljana] – Slovenia

³Faculty of Mathematics and Physics [Ljubljana] – Slovenia

Abstract

Negatively charged Nitrogen-Vacancy (NV) defects in diamond are a notable platform to study spin and magnetic related properties of any system. In this study we explore the potential of these centres in nanodiamonds (ND) for high-resolution spin sensing and temperature dependent measurement at the nanoscale. The size of nanodiamonds are an advantage to ensure that the read-out probe (NV) is always in close vicinity to any desired material on the diamond surface. Here we demonstrate the pros and cons of ND usage through the following two cases.

The spin active molecule azafullerene (C₅₉N) stands out from other fullerenes, especially when encapsulated in cycloparaphenylene (CPP) (1). The created supramolecular complex (10)CPP@C₅₉N shows desirable spin coherence times (T₁, T₂) and spin lifetime at room temperature (2), as well as having significantly higher yields than comparable fullerene-like molecules (desired for scalability) (3). We simulate the interaction between (10)CPP@C₅₉N and NV using density functional theory (DFT). Addressing the stability and coupling between the vacancy and the separated molecules allows us to identify band bending behaviour and induced charge doping effects, leading to a surface termination discussion. Experimentally using ND photoluminescence we link our calculations with optical detected magnetic resonance (ODMR), Rabi oscillations and T₁ relaxometry performed on ND mixed with azafullerene samples.

Utilising a cryostat in this NV experimental set-up we are also able to study the temperature dependence of NV properties (ODMR, Rabi, T₁). Taking as reference ND on insulator we discuss the practicality of NV in ND to detect a metallic effect, namely Johnson noise, on Au surfaces. This allows us to draw important conclusions concerning sample preparation, particle agglomeration and ND size effects.

References:

- (1) A. Stergiou et al., *Ang. Chimie Int. Ed.* 58 (49), 17745 (2019).
- (2) Y. Tanuma et al., *Nanoscale*, 13, 19946-19955, (2021).
- (3) D. Pinto et al., *Nature Communications*, 11, 6405, (2020).
- (4) Full publication list available from www.ewels.info

^{*}Speaker

Keywords: NV, Fullerene, Spin Active Molecule, DFT.

Time-Resolved Thermal Sensing using Nanodiamond Cathodoluminescence Spectroscopy

Pablo Sáenz De Santa María Modroño¹, Hugues Girard², Jean-Charles Arnault², and Gwénolé Jacopin^{*1}

¹Institut Néel – Centre National de la Recherche Scientifique, Université Grenoble Alpes, Institut polytechnique de Grenoble - Grenoble Institute of Technology, Centre National de la Recherche Scientifique : UPR2940, Institut Polytechnique de Grenoble - Grenoble Institute of Technology – France

²Nanosciences et Innovation pour les Matériaux, la Biomédecine et l'Energie – Institut Rayonnement Matière de Saclay (DRF), Institut de Chimie - CNRS Chimie, Centre National de la Recherche Scientifique – France

Abstract

As electronic devices become smaller, measuring their core properties with an adequate spatial resolution becomes increasingly more challenging. Particularly, local defects can create "hot spots" due to joule heating during operation, which can negatively affect device performance(1). Measuring device temperature and gradient under operation with an adequate spatial resolution would allow for better understanding of the mechanisms that currently limit device performance.

Our study seeks to achieve this goal by studying the cathodoluminescence (CL) properties of Nitrogen-doped nanodiamonds (ND). CL provides much larger spatial resolution than the commonly used PL thermal probes, since electrons have much shorter wavelength than photons. According to our simulations we can reach a spatial resolution of 13 nm, corresponding to the width of the electron penetration volume in nanodiamond.

Nitrogen doping leads to the formation of NV0 centres, which have a CL emission peak at a wavelength of 575 nm(2). We have already demonstrated the potential of the NV0 CL peak in nanodiamond as thermal probe(3). By measuring peak width using a Voigt profile, we are able to calculate the ND temperature in the 200 to room temperature range, with a spatial resolution of potentially up to 1 K.

Recently, we have been able to measure the heating originating from a μ LED circuit using the CL emission of ND dispersed on top of the sample. We have been able to measure the relationship between dissipated power and temperature, in both forward and reversed bias.

References

(1) Avram Bar-Cohen and Peng Wang. *Microgravity Science and Technology* **21.1** (Aug. 2009), Pg. 351–359.

^{*}Speaker

(2) N. B. Manson, *et al.* *Physical Review B* **87**. (Apr. 25, 2013), 155209

(3) Sáenz de Santa María Modroño, P., Girard, H.A., Arnault, J.-C. and Jacopin, G. *Phys. Status Solidi* (Oct. 2024) A 2400573.

Tuesday, October 14th
Sessions 5 & 6

Synthesis and surface functionalization of CVD nanodiamond containing SiV color centers for quantum sensor applications

Noemie Pham^{*1}, Benjamin Oksenberg², Carla Bittencourt³, Marie-Pierre Adam⁴, Jean-François Roch², Philippe Goldner¹, Jocelyn Achard⁵, Fabien Bénédic⁵, and Mary De Feudis^{1,6}

¹Institut de Recherche de Chimie Paris, Chimie ParisTech, UMR CNRS 8247, PSL Research University, 75005 Paris, France – PSL Université, Institut de Recherche de Chimie Paris, ChimieParisTech, UMR CNRS 8247, Paris, France – France

²Université Paris-Saclay, CNRS, ENS Paris-Saclay, CentraleSupélec, LuMIn, F-91190 Gif-sur-Yvette, France – Université Paris Saclay, ENS Paris Saclay, Centrale Supélec, CNRS – France

³Chimie des Interactions Plasma-Surface, Université de Mons, Place du Parc 22, 7000 Mons, Belgique – Belgium

⁴Université Paris-Saclay, CNRS, ENS Paris-Saclay, CentraleSupélec, LuMIn, F-91190 Gif-sur-Yvette, France – Université Paris Saclay, ENS Paris Saclay, Centrale Supélec, CNRS – France

⁵Laboratoire des Sciences des Procédés et des Matériaux, UPR CNRS 3407, Université Sorbonne Paris Nord, 93430 Villetaneuse, France – Université Sorbonne Paris Nord, LSPM, CNRS, UPR 3407, Villetaneuse, France – France

⁶CY Cergy Paris Université, 95031 Cergy-Pontoise, France – CY Cergy Paris Université – France

Abstract

The synthesis and functionalization of quantum nanodiamonds (NDs) is a key step toward technological innovation in biomedicine, cryptography, and sensing (1, 2). While the synthesis of diamond nanoparticles already poses a significant challenge due to the need for precise control over their size and purity, the effective incorporation of specific defects with well-defined quantum properties is no less demanding. Among these, the so-called silicon-vacancy (SiV) color centers present an additional difficulty, as they are typically introduced using solid-state sources (most often via post-synthesis implantation). However, they also hold great promise due to their unique properties: high photoluminescence (PL) of the zero-phonon line (ZPL), excellent photostability, reduced sensitivity to external electric fields, and an optically addressable electronic spin state (3). During the last years, we developed a consolidated protocol to synthesise high-quality NDs by microwave plasma Chemical Vapor Deposition (CVD) technique with Si impurity incorporation starting from a solid source and efficiently generating SiV color centers (4). This work presents a study of the physicochemical properties of the particle surfaces, along with a statistical analysis of particle size and species obtained via the CVD process. The NDs were characterized using various techniques, including zeta potential measurements, dynamic light scattering, and scanning electron microscopy (SEM). For the first time, experiments on the manipulation of surface terminations

^{*}Speaker

have been conducted, yielding promising results regarding their influence on the PL of the SiV ZPL. These characterizations were performed using X-ray photoelectron spectroscopy (XPS), Raman spectroscopy, and PL spectroscopy. This study paves the way for biochemical applications requiring surface functionalization, as well as for a deeper understanding and control of the neutral charge state SiV.

References

- (1) W. Liu, *et al.*, Nano Lett. 22, 7 (2022).
- (2) B. Vindole, *et al.*, Phys. Rev. B 106, 214109 (2022).
- (3) G. Bayer, *et al.*, Commun. Phys. 6, 300 (2023).
- (4) M. De Feudis, *et al.*, Adv. Mater. Interfaces 7, 1901408 (2019).

Keywords: Synthesis, surface functionalization, CVD nanodiamond, SiV color centers

Characterization of diamond electrodes with H-terminated N-doped nanolayers on B-doped films for CO₂ reduction by electrochemical impedance spectroscopy

Akira Kaga^{*1}, Kimiyoshi Ichikawa², Kan Hayashi², Tsubasa Matsumoto², Satoshi Yamasaki², Hitoshi Asakawa², Norio Tokuda², and Taro Yoshikawa^{1,2}

¹Daicel corporation – Japan

²Kanazawa University – Japan

Abstract

The increasing atmospheric concentration of carbon dioxide (CO₂) is a primary driver of global climate change, necessitating the development of efficient CO₂ conversion technologies (1). However, the electrochemical CO₂ reduction reaction (CORR) requires a high applied overpotential due to the high thermodynamic stability of CO₂ and is often accompanied by the competing hydrogen evolution reaction (HER), which reduces product selectivity. Diamond electrodes are promising for CORR as their high overpotential for HER suppresses hydrogen generation (2). Yet, selectively producing CO remains challenging, especially with diamond electrodes alone, due to the complex multi-electron/proton nature of CORR and the proximity of redox potentials for different pathways.

Hamers et al. demonstrated that electrons emitted from hydrogen-terminated diamond with negative electron affinity (NEA) under deep UV (DUV) light can selectively reduce CO₂ to CO in aqueous media (3,4). However, diamond's wide bandgap (~5.5 eV) necessitates DUV light, which is impractical for green chemistry applications. To address this, we developed a visible-light-responsive diamond-based photocatalyst. Boron-doped p-type diamond films were synthesized on detonation nanodiamond (DND) seed layers via chemical vapor deposition (5). Nitrogen atoms from DNDs were incorporated into the near-surface region, forming a heavily nitrogen-doped layer ($> 10^{21}$ atoms/cm³) with optically active states enabling sub-bandgap absorption. These states facilitate visible-light-induced electron emission from the NEA surface, driving CO₂-to-CO conversion in water (6).

In the study, to discuss the potential of such electrodes, we present the results of electrochemical impedance spectroscopy and the correlation between the resulting electrical properties of the electrodes and their CO₂-to-CO reduction performance obtained through multiple regression analysis.

1. S. Jin et al., *Angew. Chem.*, **133** (2021) 20795.

2. S. Yu et al., *Carbon*, **175** (2021) 440.

^{*}Speaker

3. L. Zhang et al., *Angew. Chem.*, **126** (2014) 9904.
4. L. Zhang et al., *Diamond & Related Materials*, **78** (2017), 24.
5. T. Yoshikawa et al., *Electrochim. Acta*, **525** (2025) 146085
6. T. Yoshikawa et al., *Carbon*, **218** (2024) 118689.

Keywords: CO reduction reaction, negative electron affinity, nitrogen doped diamond, nanodiamond electrode, electrochemical impedance spectroscopy, multiple regression analysis

Engineering Nanodiamonds for Enhanced EPR Imaging: Influence of Size, Surface Chemistry, and Paramagnetic Properties

Dimitri Stanicki^{*1}, Sarah Garifo², Philippe Mellet³, Hugues Girard⁴, Jean-Charles Arnault⁵, Yves-Michel Frapart⁶, Robert Muller^{7,8}, and Sophie Laurent^{2,9}

¹University of Mons [Belgium] – Belgium

²General, Organic and Biomedical Chemistry Unit, NMR and Molecular Imaging Laboratory, University of Mons (UMONS) – Belgium

³Centre de Résonance Magnétique des Systèmes Biologiques (CRMSB) – CNRS : UMR5536, Université de Bordeaux (Bordeaux, France) – France

⁴Nanosciences et Innovation pour les Matériaux, la Biomédecine et l'Energie, UMR CEA-CNRS 3685 – CEA, CNRS, Université Paris-Saclay, CEA Saclay 91191 Gif sur Yvette France – France

⁵NIMBE, UMR 3685 CEA-CNRS – CEA, DRF, IRAMIS, NIMBE, UMR 3685, CNRS, Université Paris-Saclay – France

⁶Paris University – Laboratoire de Chimie et Biochimie Pharmacologiques et Toxicologiques UMR 8601 – France

⁷Université de Mons, Laboratoire de RMN et Imagerie Moléculaire – Belgium

⁸Centre de Microscopie et Imagerie Moléculaire (CMMI) – Belgium

⁹Center for Microscopy and Molecular Imaging (CMMI) – Belgium

Abstract

Electron paramagnetic resonance (EPR) spectroscopy is a powerful sensitive technique for the detection of unpaired electron spins, with a wide range of applications. It enables the specific detection and quantification of radical species and can produce high-contrast, background-free images. However, the use of EPR for labeling and imaging is often limited by the poor stability of organic radicals from conventional probes, which can compromise the reliability and versatility of the technique. In this context, nanodiamonds (NDs) offer a promising alternative, thanks to their intrinsic paramagnetic centers and unique physicochemical properties, which may broaden the scope of EPR-based biomedical applications. Here, we report a preliminary demonstration of a practical spectroscopy and imaging application using nanosized diamond particles (< 18 nm) for electron paramagnetic resonance imaging (EPRI). We compare nanodiamonds produced by two commonly used synthesis methods, high-pressure high-temperature (HPHT) and detonation, highlighting their distinct physicochemical characteristics. Additionally, we examine how variations in particle size and surface treatment influence their EPR performance. Finally, we present experimental evidence defining the optimal conditions for achieving high-resolution imaging (spatial resolution $R < 1$ mm) and enhanced EPR sensitivity, thereby underscoring the potential of nanodiamonds as robust contrast agents in EPR applications.

^{*}Speaker

Keywords: EPR, Imaging, Raman spectroscopy, air, annealing

Surface-Modified Nanodiamonds for Enhanced Photocatalytic Hydrogen Generation

Yasmine Bouaouni¹, Jean-Charles Arnault¹, and Hugues Girard*¹

¹Nanosciences et Innovation pour les Matériaux, la Biomédecine et l'Energie – CEA-CNRS-Université Paris Saclay – France

Abstract

Among nanoscale semiconductors, nanodiamonds (NDs) have only recently begun to be seriously considered for photocatalytic reactions. This is due to the confusion with monocrystalline diamond which exhibits a wide bandgap (5.5 eV) and requires deep UV illumination (230 nm) to trigger its photoreactivity. At the nanometric scale, NDs possess native defects and chemical impurities like nitrogen, which introduce electronic states into the bandgap. These defects reduce the light energy required to initiate charge separation. This phenomenon has been confirmed by several studies, including one conducted by our team, which combined experimental results and Density Functional Theory (DFT) calculations (1, 2). Moreover, unlike other semiconductors, the electronic structure of NDs can be significantly modified (by several eV) by altering its surface chemistry (e.g., oxidized, hydrogenated, aminated). This allows for optimal adjustment of band alignments (3). In this context, our study focuses on the photocatalytic production of hydrogen from water splitting using nanodiamonds. Using our custom-built photocatalysis setup, we demonstrate that NDs can act as efficient photocatalysts even under solar illumination, with performances comparable to TiO (4). However, our results reveal that the surface chemistry and intrinsic properties of NDs play a key role in H₂ production, which will be discussed. As with other semiconductor photocatalysts, it is required to enhance visible light absorption and limit charge carrier recombination to optimize photocatalytic performances. This can be achieved by combining NDs with other materials (metallic nanoparticles, other photocatalysts). The second part of our study presents strategies that can be applied specifically to nanodiamonds.

Overall, this study highlights the potential of nanodiamonds as a versatile and efficient material for solar-driven photocatalytic H₂ production, paving the way for innovative applications in renewable energy technologies.

(1) F. Buchner, *Nanoscale*. 2022, 14, 17188.

(2) T. Yoshikawa, *Carbon* 2024, 218, 118689.

(3) D. Miliiaieva, *Nanoscale Adv.* 2023, 5, 4402–4414.

(4) C. Marchal et al., *Adv. Energy Sustain. Res.* 2024, 5, 1-8.

Keywords: Photocatalysis, surface chemistry, colloids

*Speaker

Optical Communication via Rabi Oscillations in NV Center Ensembles

Ziad Abi Akar^{*1} and Christophe Couteau^{*1}

¹Université de Technologie de Troyes – Laboratoire Lumière, nanomatériaux, nanotechnologies (L2n) – France

Abstract

Optical communication systems are crucial for the future of secure, high-speed data transmission, and recent advancements in quantum technologies show promising potential in revolutionizing this field. This project focuses on using **nitrogen-vacancy (NV) centers** in diamond as a medium for optical communication, with the ultimate goal of developing quantum communication schemes. The work explores the use of **microwave-induced Rabi oscillations** to control the quantum states of an NV center ensemble within a diamond sample, utilizing **Optically Detected Magnetic Resonance (ODMR)** for precise measurement and modulation.

The initial step in this research is to demonstrate basic message transmission by exploiting the **drop in photoluminescence (PL)** of NV centers induced by Rabi oscillations. In this system, **bit encoding** is achieved by **ON-OFF Keying (OOK)** modulation. This binary encoding scheme allows for the transmission of information in a quantum context, where the photoluminescence response of the NV centers serves as the key indicator for data transmission.

Through this approach, we aim to establish a proof of concept for using NV center ensembles in diamond as a foundation for optical communication systems. The precision and reliability of the ODMR technique, combined with the inherent advantages of quantum states in NV centers, provide an innovative platform for achieving robust and secure communication channels. While the current focus is on encoding and detecting basic messages, the long-term objective of this research is to extend these findings toward the development of **quantum communication systems**. By leveraging the quantum properties of NV centers, the project seeks to contribute to the broader goal of implementing secure, quantum-based optical communication networks, where the reliability and security of data transmission are enhanced by the fundamental principles of quantum mechanics.

This work not only pushes the boundaries of quantum communication but also paves the way for practical applications in quantum networks, which could become pivotal in securing the future of optical communication technologies.

Keywords: Color centers, optical communication

^{*}Speaker

NANO-DIAMOND FILMS FORMATION FROM ENERGETIC SPECIES

Alon Hoffman*¹

¹Schulich faculty of Chemistry, Technion, Israel Inst. of Technology, Haifa 32000, Israel – Israel

Abstract

Nano-diamond (ND) films are deposited by energetic using the direct-current glow-discharge CVD from a methane/hydrogen mixture. The growth occurs on top of a preferentially oriented graphitic precursor with basal planes perpendicular to the surface. These films consist of an agglomerate of diamond particles (size 3-5 nm) with amorphous grain boundaries. The hydrogen concentration in the graphitic precursor is only a few percent, however it increases to ~15-20 at.% in the film.

ND films were explored by complementary methods. The hydrogen content and its role in ND film formation were assessed. The experimental methods used comprise NEXAFS to probe the short range coordination of the carbon films and indirectly their phase composition. The surface and grain boundary phase composition were investigated by a combination of EELS measured as a function of incident electron energy and hydrogen etching experiments. By TEM the micro-structural evolution and their visualization were achieved. The density evolution of the films was determined by XRR. The hydrogen content and its distribution in the films was studied by SIMS and ERD. The hydrogen bonding was investigated by HREELS. Most likely hydrogen is bonded within the amorphous grain boundaries and saturates the ND particles. The surface of the films is amorphous in nature.

ND film and growth from energetic species is explained as a sub-surface process in terms of a four step cyclic process:

- (1) Formation of a dense, hydrogenated sp² carbon coordinated oriented layer.
- (2) Precipitation of sp³ C clusters in this graphitic phase.
- (3) Growth of ND particles up to ~5 nm in size by energetic species bombardment of the diamond / hydrogenated carbon - interface. It involves preferential displacement of sp² carbon coordinated carbon atoms leaving sp³ coordinated carbon atoms intact, leading to expansion of the diamond phase.
- (4) Frustration of growth of diamond particles.
- (5) Growth of the film formed of an agglomerate of ND particles by a cyclic process which involves process 2-4.

Keywords: nanodiamond film, microstructure

*Speaker

Bottom-up production of nanodiamonds using MW microplasma

Swaminathan Prasanna^{*1}, Abdoulaye Siby , Joel Jeevan , Arvind Bhakta , Armelle Michau , and Khaled Hassouni

¹Laboratoire des Sciences de Procédés et Matériaux (LSPM), CNRS-UPR 3407 – université Paris 13 – France

Abstract

In this study, the formation and properties of carbon nanostructures obtained from a low-pressure-low temperature microplasma operated with Ar/H₂/CH₄ gas precursors were investigated. The study reveals gas phase nucleation of nanodiamonds among other phases of carbon such as graphite and amorphous carbon. The use of plasma nucleated nanodiamonds looks promising in terms of simplicity and cost-effectiveness, and works towards a bottom-up approach of producing high-quality nanodiamonds.

Raman spectroscopy revealed that the signature of the nanostructures produced was insensitive to the nature of the substrate. The main conclusion of the study is that nucleating of nanodiamonds is sustained by high densities of H-atoms at moderate gas temperatures and optimum concentrations of hydrocarbon radicals and molecules. High densities of hydrocarbons push the equilibrium towards sp² and amorphous nanostructures even under high H-atom densities. The conditions where maximum nanodiamonds are found are also the conditions where minimum of amorphous sp² structures including transpolyacetylene and soot. The chemistry of hydrocarbons are complex and the resulting nucleation pathways are dominated by the abundance of dominant carbon radicals that are formed in the plasma. From OES of the C₂ and CH radicals and correlating with the results from Raman analysis indicates that C₂ and CH may have an important role in the nucleation of nanodiamonds. Possibility of doping the nanodiamonds with N was tested by adding small amounts of N₂O. We will discuss the applications of these nanodiamonds for growing NCD films as well as larger nanodiamonds in a conventional MW reactor used for CVD growth.

Keywords: nanodiamonds, Bottom, up synthesis, Plasma

^{*}Speaker

IMPROVED GAS PHASE NUCLEATION OF NANODIAMONDS WITH ARGON ADDITION

Joel Jeevan^{*1}, Abdoulaye Siby², Armelle Michau, Michael Redolfi³, Khaled Hassouni⁴,
and Swaminathan Prasanna⁵

¹Laboratoire des Sciences des Procédés et des Matériaux – Institut Galilée, Centre National de la Recherche Scientifique, Université Sorbonne Paris nord – France

²Laboratoire des Sciences des Procédés et des Matériaux – Institut Galilée, Université Sorbonne Paris Cité, Centre National de la Recherche Scientifique, Université Sorbonne Paris nord – France

³Université Sorbonne Paris Nord – LSPM, CNRS – UPR 3407, Université Paris 13 - Villetaneuse, France – France

⁴Laboratoire des Sciences de Procédés et Matériaux (LSPM), CNRS-UPR 3407 – université Paris 13 – France

⁵Laboratoire des Sciences des Procédés et des Matériaux – Institut Galilée, Centre National de la Recherche Scientifique : UPR3407, Université Sorbonne Paris nord, Centre National de la Recherche Scientifique – Institut Galilée, Université Paris 13, 99 avenue Jean-baptiste Clément, F-93430 Villetaneuse, France

Abstract

Nanodiamond was synthesized using Ar/H₂/CH₄ microwave microplasma torch. Microwave power, pressure, H₂/CH₄ ratio were fixed by varying Ar concentration. Plasma was characterized using optical emission spectroscopy (OES) and pico-second two absorption laser induced fluorescence (ps-TALIF)(1) for parameters such as T_g around 1500 K and nH(1) in range of 1016 - 1017 cm⁻³. Nanodiamond of highest sp³ fraction were nucleated at 100 mbar pressure with 90 Watt injected MW power, and gas composition of 96 sccm H₂, 4 sccm CH₄ and 20 sccm Ar. A direct correlation between intensity of C2 Swan band emission to sp³ fraction (Fig 1) was observed, indicating the potential role of C2 dimer in ND nucleation. The importance of C2 in ND nucleation has been observed by other researchers as well (1). The nH is increased with increasing Ar in the plasma. It is known that, nH have strong influence in sp³ fraction because it is associated with hydrogen abstraction reaction resulting in formation of CH₃ radicals(1). Even though we advocate the role of C2 dimer as a building block in ND nucleation phenomena, it is obvious that other sp³ nucleation routes through CH₃ due to high nH along with other sp² growth pathways may also co-exist.

Keywords: Nucleation, Plasma chemistry, Nanodiamond, Molecular growth, Plasma diagnostics

^{*}Speaker

Etching of Nanodiamond Seeds during Early CVD Growth: Size-Dependent Modeling and Implications for Ultrathin Diamond Film Engineering

Raffaella Salerno^{*1,2}, Alessandro Bellucci¹, Eleonora Bolli¹, Matteo Mastellone¹,
Veronica Valentini¹, Daniele Trucchi¹, Massimo Tomellini², and Riccardo Polini²

¹Istituto di Struttura della Materia – Consiglio Nazionale delle Ricerche, U.O.S. Montelibretti, Via
Salaria km 29.300, 00015 Monterotondo, Italia – Italy

²Dipartimento di Scienze e Tecnologie Chimiche, Università degli Studi di Roma Tor Vergata, Via della
Ricerca Scientifica 1, 00133 Roma, Italia – Italy

Abstract

Detonation nanodiamonds (DNDs) serve as indispensable seeding agents in the fabrication of ultrathin (≤ 100 nm) nanocrystalline diamond films. However, their stability under typical microwave chemical vapor deposition (MWCVD) plasma environments remains a limiting factor in achieving continuous ultrathin diamond coatings (1).

This study (2) offers a kinetic investigation and theoretical modeling of the etching of DND seeds during the initial stages of MWCVD diamond growth. Employing SEM to monitor surface seed density over time under controlled plasma conditions, we experimentally quantify the progressive disappearance of DND particles on Si (100) substrates. The phenomenon is analyzed through a size-dependent etching model, based on the Young–Laplace equation, taking into account the increase of the chemical potential of carbon atoms in DND particles and the consequent reduction of the activation energy for the reaction with atomic hydrogen. The model explains the experimental seed disappearance kinetics by proposing that nanodiamond particles smaller than a "critical radius", r^* , are etched away, whereas those larger than r^* can survive and grow.

Building on this understanding, the size-dependent stability of DND seeds has been harnessed to control the growth of nanocrystalline diamond films with thicknesses ≥ 40 nm on Si (100) substrates, tailored for application as cathodes in photon-enhanced thermionic emission (PETE) devices (3). Thinner films offer superior electron emission performance due to the lower resistance of the diamond film compared to thicker samples. The influence of grain boundaries on cathode performance was further investigated with Raman spectroscopy and Kelvin Probe Force Microscopy measurements indicating that an 80 nm-thick diamond film yields the highest emission current density, attributed to its favorable grain boundary distribution.

(1) M. Tomellini and R. Polini, *Diam. Relat. Mater.* 2023, 133, 109700.

(2) R. Salerno et al., *ACS Omega* 2023, 8, 25496.

(3) R. Salerno et al., *ACS Appl. Energy Mater.* 2024, 7, 868.

^{*}Speaker

Keywords: detonation nanodiamond seed etching

Wednesday, October 15th
Sessions 7 & 8

12C enriched Fluorescent Nanodiamonds for biomedical quantum sensing applications

Masazumi Fujiwara*¹

¹Okayama University – Japan

Abstract

Fluorescent nanodiamonds (FNDs) containing nitrogen-vacancy (NV) centers are emerging as robust quantum sensors for biological applications, enabling nanoscale detection of temperature and magnetic fields with high biocompatibility and photostability. I will talk about our recent progress in developing quantum-grade FNDs through isotopic (¹²C) enrichment and reduction of substitutional nitrogen impurities. The resulting FNDs, with NV concentrations of 0.6–1.3 ppm, exhibit greatly improved spin properties-achieving T₁ up to 1.6 ms and T₂ up to 5.4 μ s-while maintaining bright fluorescence (1). These enhancements allow ODMR detection with significantly reduced microwave power and enable thermal echo temperature measurements with a sensitivity of 0.28 K/sqrt(Hz). I will also talk about applications of FND quantum sensors to biological thermometry and on-chip bioassay (2, 3).

(1) K. Oshimi et al., *ACS Nano* **18**, 35202 (2024).

(2) M. Fujiwara et al., *Sci. Adv.* **6**, eaba9636 (2020).

(3) K. Oshimi et al., *Lab Chip* **22**, 2519 (2022).

Keywords: NV, quantum sensing

*Speaker

Measuring axonal transport using neurotropic fluorescent nanodiamonds

Baptiste Grimaud^{*1}, Fletcher Fletcher², Brigitte Potier¹, Régis Daniel³, Arfaan Rampersaud, William Buchmann³, and François Treussart^{*1}

¹Laboratoire Lumière, Matière et Interfaces – CentraleSupélec, Université Paris-Saclay, Centre National de la Recherche Scientifique, Ecole Normale Supérieure Paris-Saclay, Centre National de la Recherche Scientifique : UMR9024 / FRE2036, Centre National de la Recherche Scientifique : FRE2036 – France

²Columbus NanoWorks, Inc., Columbus, OH 43212 – United States

³Laboratoire Analyse, Modélisation et Matériaux pour la Biologie et l'Environnement – Université d'Évry-Val-d'Essonne, Institut de Chimie - CNRS Chimie, Université Paris-Saclay, Centre National de la Recherche Scientifique, CY Cergy Paris Université – France

Abstract

Defects in axonal transport at the molecular level are observed in neurodegenerative diseases, but their roles in the development of the pathology are unknown. We developed a method to measure axonal transport based on the endocytosis of optically active nanocrystals into neurons, followed by recording of their movement using fast video-microscopy. We first established the approach in primary neuron culture, using fluorescent nanodiamonds (FNDs) (1) and then extended it *in vivo* to the brain of a zebrafish larvae making use in that case of second harmonic generation from nonlinear nanocrystal (2). In both cases, we demonstrated that our method is sensitive enough to detect endolysosomal transport deficits induced by a small change in concentration of transport-related molecules (1,2). However, the method suffers from a low yield of internalization of the nanoparticles.

In order to enhance their endocytosis, we covalently grafted neurotropic peptides (RVG29) onto pegylated FNDs. We characterized the formation of the FND-PEG-RVG29 conjugate by infrared spectrometry and mass spectrometry (MALDI TOF), and evaluated its affinity for its target using a surface plasmon resonance biosensor. Preliminary results confirm the formation of a covalent bond.

While continuing to analyze the FND-PEG-RVG29 conjugates, we have measured the gain in internalization efficiency compared to bare FNDs. In both neuron-like cell line (N2a) and primary hippocampal mouse neuron cultures, the functionalized FNDs exhibited a 2- to 3-fold increase in the fraction of particles having a directed motion compare to bare FNDs, suggesting a same fold increase in their uptake. We are now evaluating if the uptake enhancement remains valid in more complex models, including *in vitro* stem-cell derived human neurons and *in vivo* zebrafish larva. Altogether, this system could enable precise measurements of axonal transport in relevant models of neurodegenerative diseases.

Keywords: fluorescent nanodiamonds, neurotropic peptide, mass spectrometry, axonal transport

^{*}Speaker

Nanodiamond Conjugates for Tracking Disease-Linked RNA-Binding Proteins

Marie-Odile David^{*1}, Hui Pei¹, Samia Ramdani¹, Imen Abid-Walla¹, and Ahmed Bouhss¹

¹Structure et activité des biomolécules normales et pathologiques – Université d'Évry-Val-d'Essonne, Institut National de la Santé et de la Recherche Médicale, Université Paris-Saclay – France

Abstract

Neurodegenerative diseases, such as ALS and FTLT, are characterized by the progressive degeneration of neurons, leading to irreversible motor and cognitive impairments. These disorders remain largely incurable, with complex molecular mechanisms still under investigation. Among the proteins implicated in these diseases, the RNA-binding protein FUS has gained attention due to its propensity to aggregate and its involvement in pathological cellular processes. To better understand FUS behavior over time in living cells, this project explores the use of fluorescent nanodiamonds (fNDs) as permanent, non-toxic, and photostable labels for bioimaging. The objective is to chemically link FUS to fNDs in a way that preserves its biological activity and allows for long-term intracellular tracking. Several strategies for constructing and characterizing the fND–FUS complex were developed, focusing on stability, specificity, and efficient cellular delivery. Preliminary experiments validated the potential of this approach, laying the groundwork for future studies on the dynamic behavior of FUS in neurodegeneration.

Keywords: Neurodegenerative diseases, RNA, binding proteins, Fluorescent nanodiamonds (fND), Chemical conjugation, bioimaging

^{*}Speaker

Fluorescent Nanodiamond-based delivery systems for mitochondrial targeting of bioactive molecules

Dorna Akbarzadeh^{1,2}, Juan-Carlos Calderón De La Rosa², Marie-Odile David³, François Treussart⁴, Nazanine Modjtahedi⁵, and Giorgia Urbinati^{*1,2}

¹Unité de Technologies Chimiques et Biologiques pour la Santé – Institut National de la Santé et de la Recherche Médicale, Centre National de la Recherche Scientifique, Université Paris Cité – France

²Aspects métaboliques et systémiques de l'oncogénèse pour de nouvelles approches thérapeutiques – Institut Gustave Roussy, Université Paris-Saclay, Centre National de la Recherche Scientifique – France

³Structure et activité des biomolécules normales et pathologiques – Université d'Évry-Val-d'Essonne, Institut National de la Santé et de la Recherche Médicale, Université Paris-Saclay – France

⁴Laboratoire Lumière, Matière et Interfaces – CentraleSupélec, Université Paris-Saclay, Centre National de la Recherche Scientifique, Ecole Normale Supérieure Paris-Saclay, Centre National de la Recherche Scientifique : UMR9024 / FRE2036, Centre National de la Recherche Scientifique : FRE2036 – France

⁵Unité Physiopathologie et Génétique du Neurone et du Muscle – UMR CNRS 5261, Inserm U1315, Université Claude Bernard Lyon1 – France

Abstract

Metabolic plasticity and mitochondrial function play central roles in tumorigenesis and cancer cells' responses to anti-cancer therapies, making mitochondria a critical target for pharmacological intervention (1–2). If they accumulate in the mitochondria in effective doses, bioactive molecules that modulate mitochondrial activity could offer the prospect of new therapies (3–4). These molecules can be vectorized into mitochondria using nanovectors, to improve their bioavailability and reduce off-target effects (5). In this context, nanometric size delivery systems have gained significant interest due to their ability to enhance bioavailability of therapeutic agents by means of targeting specific cells or subcellular compartments (6).

Our team has focused its attention on the design and application of fluorescent nanodiamonds (FND) as carriers for bioactive molecules. The FNDs have emerged as promising nanocarriers due to their excellent biocompatibility, intrinsic fluorescence, and chemically versatile surfaces, which enable the loading of bioactive molecules and their delivery to subcellular compartments (7).

The aim of this work is to functionalize FND with a mitochondrion-targeting moiety in order to deliver to this organelle therapeutic molecules.

In this study, FNDs were coated with two different PEG-chains carrying different functional groups. The azide moiety was used to conjugate the mitochondrion-targeting peptide SS20 *via* copper-free click chemistry; the amines groups were used to complex the bioactive peptide N27 *via* electrostatic interactions (Figure 1). The N27, identified as a promising inhibitor of the AIF/CHCHD4 mitochondrial import pathway, has been chosen for the proof

*Speaker

of concept (8).

This mitochondrion-targeting FNDs have been formulated. Their physicochemical characterisations as well as their cellular and subcellular localisation have been investigated and will be presented.

References:

1. Hanahan D, et al., doi: 10.1016/j.cell.2011.02.013
2. Weinberg SE, doi: 10.1038/nchembio.1712
3. Battogtokh G, et al., doi: 10.1016/j.apsb.2018.05.006
4. Shim G, et al., doi : 10.1016/j.addr.2024.115411
5. McClements DJ, doi: 10.1016/j.cis.2018.02.002
6. Adepu S, et al., doi : 10.3390/molecules26195905
7. Chauhan S, et al., doi: doi: 10.1016/j.jpha.2019.09.003
8. Hangen E, et al., doi : 10.1016/j.molcel.2015.04.020

Keywords: Nanovectorization, fluorescent nanodiamonds, mitochondria, targeting, bioactive molecules

Nanodiamond Scintillator: A Novel Approach to Profiling EUV and Soft X-ray Beams for Photolithography

Mark Yuen Yung Hui^{*1}, Pei-Jie Wu², Teng-I Yang³, and Huan-Cheng Chang²

¹Institute of Atomic and Molecular Sciences, Academia Sinica, Taipei 106, Taiwan – Taiwan

²Institute of Atomic and Molecular Sciences, Academia Sinica, Taipei 106, Taiwan – Taiwan

³Taiwan Instrument Research Institute, National Applied Research Laboratories, Hsinchu City 300092, Taiwan – Taiwan

Abstract

Extreme ultraviolet (EUV) radiation with wavelengths of 10–121 nm has been applied in photolithography to fabricate nanoelectronic chips. This study uncovers the practical potential of fluorescent nanodiamonds (FNDs) coatings on optical image sensors for detecting extreme ultraviolet (EUV) and soft X-ray (SXR) radiation. We applied electrospray deposition to produce a uniform carbon-based scintillator thin film on indium tin oxide (ITO) coated substrates, with typical film thickness of $\sim 1 \mu\text{m}$. Red fluorescence was observed from neutral nitrogen-vacancy centers of the FND film, when exposed to the synchrotron radiation beam (80–1400 eV). The FND fluorescence was further collected by a fiber optic plate (FOP) to a visible light camera for imaging and beam diagnostics. Compared with a f/1 lens-coupled system, the fiber-coupled device was about eight times more sensitive. This research underscores the promising application of FND coatings by electrospray deposition as a cost-effective and versatile strategy for viewing, sensing and imaging EUV/SXR radiation, which can significantly advance the field of next generation nanoelectronics.

Keywords: nanodiamonds, color centers, imaging, sensing

^{*}Speaker

Surface tuning of nanodiamonds: investigating the impact of surface modifications for applications in radiosensitization

Sofia Sturari^{*1,2}, Nour-Hanne Amine^{1,2}, Ilaria Andreana³, Pietro Aprà², Silvia Arpicco³, Valeria Bincoletto³, Stefano Boetti^{3,4}, Adam Britel^{1,2}, Maria Paula Cabral Campello^{5,6}, Elisabetta Alessandra Durisi^{1,2}, Simona Giordanengo², Edgar Mendes^{5,6,7}, Lorenzo Mino⁸, Diango Manuel Montalvan Olivares^{1,2}, Valeria Monti^{1,2}, Teresa Pinheiro^{5,7}, Chiara Riganti⁴, Giulia Tomagra³, Anna Vignati^{1,2}, Beatrice Zurletti³, and Federico Picollo^{1,2}

¹Physics Department, University of Torino – Italy

²National Institute of Nuclear Physics, sect. Torino – Italy

³Department of Drug Science and Technology, University of Torino – Italy

⁴Department of Oncology, University of Torino – Italy

⁵Department of Engineering and Nuclear Sciences, Instituto Superior Técnico, University of Lisbon – Portugal

⁶Center of Sciences and Nuclear Technologies, Instituto Superior Técnico, University of Lisbon – Portugal

⁷Institute of Bioengineering and Biosciences, Instituto Superior Técnico, University of Lisbon – Portugal

⁸Chemistry Department, University of Torino – Italy

Abstract

Enhancing cancer cell radiosensitivity is essential for improving radiotherapy efficacy without increasing radiation dose. Radiosensitizers, which amplify ionizing radiation effects on tumor cells, offer a promising strategy to achieve this goal. However, identifying agents that combine high effectiveness with biocompatibility remains challenging. Nanodiamonds (ND) represent a viable solution due to their excellent biocompatibility and the possibility of tailoring their surface to enhance reactive oxygen species (ROS) production under irradiation. This effect can be achieved by promoting the formation of hydrogen terminations or decorating the surface with gold nanoparticles. Moreover, functionalization with hyaluronic acid (HA) improves ND dispersibility in aqueous media and enables targeting of tumor cells overexpressing HA receptors, such as pancreatic adenocarcinoma cells.

In this study, we investigated the applicability of ND as radiosensitizers by evaluating their effect on hydroxyl radical ($\bullet\text{OH}$) generation in aqueous solution induced by γ -photons (15 MV) or electrons (10 MeV) delivered with the Elekta SL 18 MV linear accelerator of the University of Torino Physics Department and the National Institute of Nuclear Physics of Torino. To assess the impact of different surface treatments, we compared hydrogenated (NDH), gold-functionalized (Au-ND), and hyaluronan-coated (HA-ND) ND with unmodified ND. Terephthalic acid was employed as fluorogenic probe to detect $\bullet\text{OH}$ species, based

*Speaker

on its hydroxylation reaction yielding fluorescent 2-hydroxyterephthalic acid, allowing indirect $\bullet\text{OH}$ quantification *via* fluorescence spectroscopy. Additionally, clonogenic assays on radio-resistant pancreatic cancer cells were performed following co-treatment with ND and radiation to assess possible biological effects.

Our results show that NDH, HA-NDH, and Au-ND increase $\bullet\text{OH}$ generation and induce greater reductions in cell survival. These findings suggest a correlation between ROS enhancement and radiosensitization, thus highlighting the potential of ND in therapeutic applications.

Keywords: Nanodiamonds, Radiosensitizers, Surface functionalization, Radicals production, Radioresistant cancer cells treatment

Precision Engineering of Immunocellular States via Intracellular Fever with Nanodiamond Composites

Yingke Wu^{*1}, Kaiqi Wu¹, Kazem Ebadi-Jalal², Toszka Bohn², and Tanja Weil¹

¹Max Planck Institute for Polymer Research – Germany

²University Medical Center of the Johannes Gutenberg University Mainz – Germany

Abstract

Temperature plays a vital role in cellular function, affecting numerous processes such as enzymatic activity, signal transduction, and immune responses. However, explicitly correlating intracellular temperature with cellular function is challenging, due to the lack of availability of precisely manipulating and monitoring the nanoscale local temperatures. Herein, a photostable photothermal croconium dye (CR) was designed and synthesized to work as a light-controlled intracellular heater, then the CR was conjugated with nanodiamonds containing nitrogen-vacancy (NV) centers, working as nanothermometer, to develop a novel nanodiamond composite(FNDNG-CR-PEG). It enables real-time manipulation and monitoring of intracellular temperatures within macrophages. The relationship between intracellular fever and macrophage polarization was studied using immunofluorescence microscopy and flow cytometry for the first time. Furthermore, the amount of local free radical species induced by local temperature change was monitored by integrating the T1 relaxometry of nanodiamonds. The transcriptomics was further carried out to understand the intracellular fever influence on phenotype at the genome level. This nanodiamond composite provide a powerful platform for exploring the interplay between intracellular thermal regulation, redox signaling, and immune cell behavior. This study not only advances the understanding of intracellular thermal dynamics but also suggests new approaches for enhancing the efficacy of photothermal therapies and modulating immune responses at the nanoscale.

Keywords: Nanodiamond, temperature sensing, temperature manipulation, macrophage polarization

^{*}Speaker

Hybrid Nanozyme Systems based on Gold-Decorated Nanodiamonds for Advanced Electrochemical Sensing and SERS substrate.

Orlanducci Silvia*¹

¹Dipartimento di Scienze e Tecnologie Chimiche, Università degli Studi di Roma Tor Vergata [Roma, Italia] = University of Rome Tor Vergata [Rome, Italy] = Université de Rome Tor Vergata [Rome, Italie] – Italy

Abstract

Nanozymes, which are nanomaterials exhibiting enzyme-like catalytic properties, have garnered significant interest in the realm of electrochemical sensing due to their remarkable stability, reusability, efficiency under extreme conditions, and cost-effectiveness compared to natural enzymes. Gold nanoparticles (AuNPs) have shown exceptional peroxidase-like activity, making them particularly appealing for sensing applications. However, traditional methods for synthesizing gold nanoparticles come with several drawbacks, including the use of reducing and stabilizing agents that can negatively impact the material's catalytic performance. Therefore, developing innovative synthesis strategies is crucial for enhancing catalytic efficiency and improving sensor performance. In this study, we investigate the potential of gold-decorated nanodiamonds as a novel platform for electrochemical sensors, biosensors, and surface-enhanced Raman spectroscopy (SERS). By decorating nanodiamonds with AuNPs, we create a hybrid system that exhibits enhanced catalytic properties, as demonstrated by UV-vis spectrophotometry, and a significant effect as SERS substrate using near infrared laser source. This AuNP-ND hybrid demonstrates significant peroxidase-like activity while benefiting from increased operational stability. To adapt this system for electrochemical applications, we incorporated the hybrid materials onto the surface of graphite working electrodes within screen-printed electrodes on PET substrates. Electrochemical characterization revealed a strong synergistic effect, resulting in enhanced electron transfer, improved sensitivity, and robust performance under operational conditions. This study positions nanodiamonds as a valuable new support for nanozyme-based electrochemical sensors, paving the way for innovative, enzyme-free detection strategies in both environmental and biomedical contexts.

M. Zandieh, J. Liu. *Advanced Materials*, 2024, vol. 36, pp. 2211041, doi:10.1002/adma.202211041.

- J. Lou-Franco, B. Das, C. Elliott, C. Cao. *Nanomicro Lett*, 2021, vol. 13, n.10, doi:10.1007/s40820-020-00532-z. S. Orlanducci, et al. *ACS Applied Optical Materials*, 2024, vol. 2, pp. 1180–1187, doi:10.1021/acsaom.4c00132.

- G. Reina, et al. *Physica Status Solidi (C) Current Topics in Solid State Physics*, 206, vol. 13, pp. 972–978, doi:10.1002/pssc.201600111.

- S. Orlanducci. *Eur J Inorg Chem*, 2018, vol. 48, pp. 5138–5145, doi:10.1002/ejic.201800793.

Keywords: gold nanoparticles, Nanodiamonds, Nanozymes, electrochemical sensor, SERS

*Speaker